



**Mascoat**  
WEATHERBLOC-IC



## Selection & Specification Data

<b>Product Name</b>	Mascoat WeatherBloc-IC
<b>Product No.</b>	MWB-IC
<b>Description</b>	Mascoat WeatherBloc-IC is a water based acrylic coating comprised of air-encapsulated, insulating particles that produce thermal insulation qualities. It is specifically designed for rooftops, warehouses, barns, storage areas, mobile homes, portable buildings, containers, coolers, walls and sheds.
<b>Features</b>	<ul style="list-style-type: none"> <li>◆ Excellent thermal insulation at low thickness</li> <li>◆ Excellent solar reflectance</li> <li>◆ Excellent application characteristics</li> <li>◆ Fast recoat times</li> <li>◆ Helps deaden sound</li> <li>◆ Applies to almost any surface</li> <li>◆ No VOC Product</li> <li>◆ Helps to seal walls and membranes</li> <li>◆ Provides anti-condensation protection</li> </ul>
<b>Base</b>	Water-based Acrylic Insulation Coating
<b>Gloss</b>	Flat
<b>Priming</b>	Self priming over non-ferrous materials (stainless steel & aluminum). Primers required for carbon steel substrates.
<b>Topcoats</b>	Please consult Mascoat
<b>Wet Weight</b>	6.4 lbs/gallon (0.74 kg/liter)
<b>Weight Dry Film To Area</b>	0.049 lbs/ft <sup>2</sup> at 20 mils DFT (0.241 kg/m <sup>2</sup> at 0.50 mm DFT)
<b>Practical Volume Solids Content</b>	70–72%
<b>Average Coat Thickness</b>	20–22 mils WFT at 70°–130°F (0.5 mm WFT at 21°–54°C)
<b>Practical Dry Coat Coverage</b>	47–52 ft <sup>2</sup> /gallon @ 20 mils (1.22 m <sup>2</sup> /liter @ 0.5 mm)
<b>VOC Content</b>	0.05 lbs/gallon (5.9 g/liter)
<b>Limitations</b>	Applications should not exceed 200°F (93°C).
<b>Storage</b>	Do not subject wet coating in pail form to freezing conditions. Coating should be kept in a warehouse between 60°F and 90°F.

## Substrates & Surface Protection

<b>Surface Prep</b>	Surface should be dry and free of foreign matter. Surface prep can be used to NACE 1-3 (SSPC SP 5-6) when applicable.
<b>Ferrous Surfaces</b>	Should be primed prior to application of MWB-IC Insulating Coating. Since the coating is water-based, it is important to have a boundary layer of protection to prevent flash rusting.
<b>Non-ferrous Surfaces</b>	The coating can be applied directly to non-ferrous surfaces. Surface should be clean and free of any oil, dirt or other foreign matter.

## Application Equipment

Listed below are the general equipment guidelines for the application of this product.

<b>Airless Sprayer</b>	Pump Ratio:	33:1 or larger
	Volume:	1.5 gpm (5.7 lpm) or greater
	Hose:	3/8" or larger with no more than 3' of 1/4" whip. 1/2" hose recommended for length above 50'.
	Tip Size:	0.017" (for tight spots) 0.019–0.023" (Normal use)
	Pressure:	Minimum of 3000 PSI
<b>Small Spray Application</b>	Please consult Mascoat for the Small Application Sprayer. This sprayer is excellent for small applications and touch-ups.	
<b>Brush</b>	Brushing is only recommended for touch-up of less than 0.5 ft <sup>2</sup> (0.04 m <sup>2</sup> ). Brushing can inhibit coating performance. Please consult Mascoat for detailed brushing instructions.	
<b>Rolling</b>	Not recommended for this coating.	

## Application Conditions

<b>Surface Temperatures</b>	Surface temperatures for applications should be greater than 50°F (10°C) or above. Lower surface temperatures will increase dry times.
<b>Applications</b>	<p><i>Ambient &amp; Cold (60°–139°F, 15°–59°C):</i> For temperatures (surface or ambient – whichever is lower), an initial tack coat is recommended of 10 mils (0.25 mm or 250 microns). This tack coat will help eliminate sag on vertical wall applications. Tack coat should be dry to touch prior to next pass. Typical coat thickness should not exceed 20–22 mils (0.5–0.55mm) wet. Coating can be reapplied after each coat is thoroughly dry.</p> <p><i>Hot (&gt;140°F, &gt;60°C):</i> Please consult Mascoat.</p>
<b>Application Thickness</b>	Product can be applied in successive coats to increase insulation ability. There are no upper limitations.
<b>Dryfall</b>	Dryfall within a 3 ft radius.

## Other Coating Specifications

Item	English Value (Metric Value)	Test Method
Cyclic Salt Fog	Excellent 2000 hrs	ASTM B-117
UV-A Exposure	Excellent 2000 hrs	ASTM D-5894
Humidity Cabinet	Excellent 2000 hrs	ASTM D-4585
QUV	Excellent 2000 hrs	ASTM G-154
Cross Hatch Adhesion	100% 5 B	ASTM D-3359
Pull Apart Strength	300–340 psi	ASTM D-4541
Elongation Rate	Above 600%	ASTM D-638
Thermal Emittance	0.86	ASTM C-1371
Solar Reflectance	0.84	ASTM C-1549
Transmittance	0.00	Calculated
Emmissivity/ Absorptance	0.16	Calculated
Flame Spread	Class A	ASTM E-84/87
Smoke Developed	Class A	ASTM E-84/87
Cone Calorimeter	>6	ASTM E-1384-97

## Mixing & Thinning

- Mixing** Only a mud mixing paddle should be used. Use 1/2" drill motor to stir contents with paddle. *Make sure drill is set to reverse to ensure that the paddle will not mar the bucket's inner wall.* Please consult Mascoat for paddle, if needed. **DO NOT MECHANICALLY SHAKE.**
- Thinning** DO NOT THIN unless authorized in writing by Mascoat.
- Pot life** Coating is one part, so no catalyzation is needed. Pail can be reused if properly sealed.
- Container** 5 gallon pail (18.92 liters)

## Package, Handling & Storage

- Container Wet (with pail/lid)** 33.1 lbs/5 gallon pail (15.01 kg /18.92 liters)
- Net Contents** 31.0 lbs/5 gallon pail (14.06 kg/18.92 liters)
- Flash Point (Setaflash)** None
- Storage** Do not subject wet coating in pail form to freezing conditions. Coating should be kept in a warehouse between 60°F and 90°F.
- Shelf Life** 18 month shelf life from manufacture date.
- Caution** Do not let product freeze.

## Cleanup & Safety

- Cleanup** Equipment may be cleaned with soap & water.
- Safety** Half-face respirator recommended with ammonia cartridge or better. Eye protection recommended.
- Ventilation** Recommended for constricted areas.
- Caution** This material is not for human consumption.
- Clothing** Safety clothing & gloves are recommended.

## Dry Times vs. Humidity

Surface Temperature	% Humidity	Time Between Coats (hours)
51–60°F (10–15°C)	10–30%	6.00
	31–50%	8.00
	51–70%	10.00
	>70%	12.50
61–70°F (16–21°C)	10–30%	4.00
	31–50%	5.50
	51–70%	6.50
	>70%	8.00
71–80°F (22–26°C)	10–30%	2.00
	31–50%	3.00
	51–70%	3.50
	>70%	4.00
81–90°F (27–32°C)	10–30%	1.50
	31–50%	2.00
	51–70%	2.50
	>70%	3.00
91–100°F (33–37°C)	10–30%	1.25
	31–50%	1.50
	51–70%	1.75
	>70%	2.00
101–110°F (38–43°C)	10–30%	1.00
	31–50%	1.25
	51–70%	1.50
	>70%	1.75
111–120°F (44–49°C)	10–30%	0.75
	31–50%	1.00
	51–70%	1.25
	>70%	1.50
121–130°F (50–54°C)	10–30%	0.50
	31–50%	0.75
	51–70%	0.75
	>70%	1.00

Use 90° thumb test or moisture meter prior to recoat. This is the estimated dry time for 15–20 mils (0.38–0.50 mm) of Mascoat WeatherBloc-IC wet. Dry time may vary depending on other conditions such as wind or enclosed environments. Lighter thickness passes will expedite dry times. Forced ventilation in confined areas will also expedite dry times.

## Cure Times

Temperature	Cure Time
50–60°F (10–15°C)	20–24 days
61–70°F (16–21°C)	16–20 days
71–80°F (22–26°C)	12–18 days
81–90°F (27–32°C)	8–12 days
91–100°F (33–37°C)	5–8 days
>100°F (>37°C)	2–5 days

The data within is true to the best of our knowledge on the date of publication and is subject to change without prior notice. We guarantee our products to conform to Mascoat quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. All logos are property of their respective owners.

